

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau




(43) International Publication Date
1 November 2001 (01.11.2001)

PCT

(10) International Publication Number
WO 01/82390 A1

- (51) International Patent Classification⁷: **H01L 51/20** (74) Agent: **ZISK, Matthew, B.**; Skadden, Arps, Slate, Meagher & Flom LLP, New York, NY 10036 (US).
- (21) International Application Number: **PCT/US01/09623**
- (22) International Filing Date: **23 March 2001 (23.03.2001)**
- (25) Filing Language: **English**
- (26) Publication Language: **English**
- (30) Priority Data:
60/199,386 25 April 2000 (25.04.2000) US
09/784,378 15 February 2001 (15.02.2001) US
- (71) Applicant: **EMAGIN CORPORATION [US/US]**; eMagin Corporation, 2070 Route 52, Hopewell Junction, NY 12533 (US).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published:
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: **THIN FILM ENCAPSULATION OF ORGANIC LIGHT EMITTING DIODE DEVICES**



(57) Abstract: The present invention is directed to an OLED display device including an encapsulation assembly and methods for making such devices. The encapsulation assembly includes at least two layers, one of which is a dielectric oxide layer directly in contact with at least part of a substrate, and the other of which is preferably a polymer layer.



WO 01/82390 A1

TITLE OF THE INVENTION

**THIN FILM ENCAPSULATION OF ORGANIC
LIGHT EMITTING DIODE DEVICES**

5

CROSS-REFERENCE TO RELATED APPLICATIONS

This application claims priority to United States Provisional Patent Application No. 60/199386, filed April 25, 2000.

STATEMENT REGARDING FEDERALLY SPONSORED
RESEARCH AND DEVELOPMENT

10

Not applicable.

BACKGROUND OF THE INVENTION

The present invention relates to organic light emitting diode ("OLED") devices.

Typical OLED devices use small molecule and polymer organic layers having many desirable properties but that are, at the same time, oxygen- and moisture-sensitive. If oxygen or water molecules reach these layers, the operational lifetime of the OLED device can be shortened significantly. It is thus desirable to provide a barrier as part of the device structure to prevent ambient moisture and oxygen from reaching the sensitive layers.

20

OLED devices have been known for approximately two decades. All OLEDs work on the same general principles. An OLED device is typically made up of a stack of thin layers formed on a substrate. In the stack, a light-emitting layer of a luminescent organic solid, as well as adjacent semiconductor layers, are sandwiched between a cathode and an anode. The light-emitting layer may be selected from any of a multitude of fluorescent organic solids. Any of the layers, and particularly the light-emitting layer, may consist of multiple sublayers. Such devices are well known and understood by those skilled in the OLED art.

25

In a typical OLED, either the cathode or the anode is transparent. The cathode is typically constructed of a low work function material. The holes are typically injected from a high work function anode material into the organic material via a hole transport layer. The films may be formed by evaporation, spin casting or other appropriate polymer film-forming techniques, or chemical self-assembly. Thicknesses typically range from a few monolayers to about 1 to 2,000 angstroms.

BRIEF SUMMARY OF THE INVENTION

The present invention is directed to an encapsulation assembly for an organic light emitting diode display device having a substrate, and at least one organic light emitting diode device formed thereon. The encapsulation layer is formed over the substrate and the at least one organic light emitting diode device. The encapsulation layer includes a first encapsulation layer formed directly on the substrate and the organic light emitting diode device, and a second encapsulation layer formed on the first encapsulation layer.

In accordance with one embodiment of the present invention, the first encapsulation layer is an oxide layer and the second encapsulation layer is a polymer layer. The polymer layer may include parylene.

In accordance with another embodiment of the present invention, the first encapsulation layer is a polymer layer and the second encapsulation layer is an oxide layer. At least a portion of the second encapsulation layer contacts the substrate. The second encapsulation layer preferably contacts the substrate around a perimeter of the substrate.

The present invention is also directed to a method of encapsulating an organic light emitting diode display device. The method in accordance with the present invention includes the steps of forming a first encapsulation layer directly on the substrate and the at

least one organic light emitting diode device, and forming a second encapsulation layer on at least the first encapsulation layer.

In accordance with one embodiment of the present invention, the step of forming the first encapsulation layer includes the step of depositing an oxide layer directly on the substrate and the at least one organic light emitting diode device. It is contemplated that the step of depositing the oxide layer may include one of atomic layer epitaxy (ALE) or atomic layer deposition (ALD) processing to deposit the oxide layer (ALD is also known as atomic layer CVD or ALCVD). The step of forming the second encapsulation layer includes the step of depositing a polymer layer on the first encapsulation layer. This step may be performed at room temperature.

In accordance with another embodiment of the present invention, the step of forming the first encapsulation layer includes the step of depositing a polymer layer directly on a portion of the substrate and the at least one organic light emitting diode device. The step of forming the second encapsulation layer includes the step of depositing an oxide layer over the first encapsulation layer and a portion of the substrate. At least a portion of the second encapsulation layer contacts the substrate.

Thus, the present invention is directed to an organic light emitting diode display device comprising a substrate, at least one organic light emitting diode device formed thereon, and an encapsulation assembly formed over the substrate and the at least one organic light emitting diode device, the encapsulation assembly comprising: a first encapsulation oxide layer comprising a dielectric oxide, wherein the dielectric oxide of the encapsulation oxide layer lies over and in direct contact with both the substrate and the at least one organic light emitting diode device; and a second encapsulation layer, wherein the second encapsulation layer covers the first encapsulation layer.

The present invention is also directed to an organic light emitting diode display de-

vice comprising a substrate, at least one organic light emitting diode device formed thereon, and an encapsulation assembly formed over the substrate and the at least one organic light emitting diode device, the encapsulation assembly comprising: a first encapsulation oxide layer comprising a dielectric oxide deposited using a process selected from the group consisting of ALE and ALD (ALD is also known as ALCVD), wherein the dielectric oxide of the first encapsulation oxide layer lies over and is in direct contact with both the substrate and the at least one organic light emitting diode device; and a second encapsulation layer comprising a polymer, wherein the second encapsulation layer covers the first encapsulation layer. The second encapsulation polymer layer of this device preferably comprises a parylene, and in particular, parylene N, parylene C, or parylene D, and more preferably comprises parylene C. Furthermore, the dielectric oxide of the oxide layer preferably comprises Al_2O_3 , SiO_2 , TiO_2 , ZrO_2 , MgO , HfO_2 , Ta_2O_5 , aluminum titanium oxide, and tantalum hafnium oxide, more preferably comprises Al_2O_3 or SiO_2 , and most preferably comprises Al_2O_3 .

15 The present invention is also directed to an organic light emitting diode display device comprising a substrate, at least one organic light emitting diode device formed thereon, and an encapsulation assembly formed over the substrate and the at least one organic light emitting diode device, the encapsulation assembly comprising: a patterned first encapsulation layer wherein the pattern of the first encapsulation layer leaves a perimeter of the substrate exposed around the at least one organic light emitting diode device; and a second encapsulation layer comprising an ALE dielectric oxide or an ALD dielectric oxide, wherein the second encapsulation layer covers both the exposed perimeter of the substrate and the first encapsulation layer. Preferably, the first encapsulation layer comprises a polymer, and more preferably, that polymer comprises a parylene, and in particular, parylene N, parylene C, or parylene D. Most preferably, that polymer comprises parylene

C.

The present invention is also directed to an upwardly emitting organic light emitting diode display device comprising a substrate, at least one organic light emitting diode device formed thereon, and an encapsulation assembly formed over the substrate and the
5 at least one organic light emitting diode device, the encapsulation assembly comprising: a first encapsulation oxide layer comprising Al_2O_3 deposited using a process selected from the group consisting of ALE and ALD, wherein the Al_2O_3 of the first encapsulation oxide layer lies over and is in direct contact with both the substrate and the at least one organic light emitting diode device; and a second encapsulation polymer layer, wherein the second
10 encapsulation layer comprises parylene C and covers the first encapsulation layer. Optionally, this device may further comprise a layer of SiO_2 , wherein the layer of SiO_2 covers the second encapsulation polymer layer. Preferably, the first encapsulation oxide layer is substantially pure, and consists essentially of Al_2O_3 . Also preferably, the second encapsulation layer consists essentially of parylene C.

15 The present invention is also directed to a method of encapsulating an organic light emitting diode display device, wherein the organic light emitting diode display device comprises a substrate, and at least one organic light emitting diode device formed thereon, the method comprising the steps of: depositing a first encapsulation dielectric oxide layer using a method selected from the group consisting of ALE and ALD, wherein the encapsu-
20 lation dielectric oxide layer lies over and in direct contact with both the substrate and the at least one organic light emitting diode device; and depositing a second encapsulation layer, wherein the second encapsulation layer covers the first encapsulation layer.

A second method of encapsulating an organic light emitting diode display device is also part of the present invention, wherein the organic light emitting diode display device
25 comprises a substrate, and at least one organic light emitting diode device formed thereon,

the method comprising the steps of: depositing a first encapsulation dielectric oxide layer using a method selected from the group consisting of ALE and ALD, wherein the first encapsulation oxide layer lies over and is in direct contact with both the substrate and the at least one organic light emitting diode device; and depositing a second encapsulation polymer layer, wherein the second encapsulation layer covers the first encapsulation layer. Preferably, the step of depositing the oxide layer uses ALD. In this method, the step of depositing the second encapsulation polymer layer may be performed with each of the substrate, the at least one organic light emitting device thereon and the first dielectric oxide encapsulation layer at room temperature. Preferably in this method, the step of depositing the second encapsulation polymer layer further comprises a step of forming vapor phase monomer species able to condense and polymerize on the first dielectric oxide encapsulation layer at a temperature less than about 40 °C, and most preferably, at about room temperature.

It is to be understood that both the foregoing general description and the following detailed description are exemplary and explanatory only, and are not restrictive of the invention as claimed. The accompanying drawings, which are incorporated herein by reference and which constitute apart of this specification, illustrate certain embodiments of the invention, and together with the detailed description serve to explain the principles of the present invention.

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWING

Fig. 1 is a cross sectional view of a plurality of OLED devices on a single substrate having an encapsulation assembly in accordance with an embodiment of the present invention;

Fig. 2 is a cross sectional view of an OLED device resulting from dicing of the plurality of devices depicted in Figure 1;

Fig. 3 is a cross sectional view of a plurality of OLED devices on a single substrate having an encapsulation assembly in accordance with another embodiment of the present invention;

Fig. 4 is a cross sectional view of an OLED device resulting from dicing of the plurality of devices depicted in Figure 3; and

Fig. 5 is a top view of a plurality of partially constructed OLED devices on a single substrate having a partial encapsulation assembly according to an embodiment of the present invention, and showing the locations where the substrate of the finished device are to be cut during the dicing operation.

DETAILED DESCRIPTION OF THE INVENTION

The present invention is directed to OLED devices having a multilayer encapsulation assembly. While not limited to such devices, the encapsulation assembly used in the present invention is particularly well-suited for the fabrication of full-color displays, and particularly full-color miniature OLED displays. Fabrication of color OLED displays generally requires side-by-side patterning of red, green and blue sub-pixels. Since these devices are extremely moisture sensitive, any kind of wet processing directly on the OLED stack is normally not possible. Use of shadow masks during evaporation of organic materials to pattern the colors is not feasible for high resolution displays. As such, most color OLED devices are fabricated using either color filters or color changing media (CCM) that are typically patterned on a separate substrate. In order to be able to fabricate color filters on OLED substrates, which involves various wet chemical processing, it is necessary to hermetically encapsulate the OLED device layers.

In the case of full color OLED display fabrication using color filters or CCM on a separate face plate, it is important that the face plate be aligned to the device plate with very high precision. In the case of high resolution miniature displays, for example, the

alignment accuracy can be as high as $\sim 0.5 \mu\text{m}$. In addition, the gap between the two substrates needs to be minimized in order to avoid color cross-talk between the sub-pixels (especially because the OLED device emission is Lambertian). Furthermore, the two substrates need to be perfectly parallel to each other so that no undesirable effects such as
5 Newton's rings, etc. affect the display performance.

The encapsulation assemblies of the OLED devices of the present invention always have an oxide layer in direct contact with the substrate. This contact forms a perimeter around the OLED stacks and a barrier against moisture incursion. preferably, the oxide layer or layers of the present invention are formed using atomic layer epitaxy (ALE) or by
10 atomic layer deposition (ALD). ALD is also sometimes referred to a atomic layer chemical vapor deposition or ALCVD, and the two terms are used interchangeably herein. ALE, and ALD oxide layers are conformal and avoid the propagation of defects due to uneven substrate surfaces, and thus form adequate barriers against moisture incursion.

A first embodiment of the present invention is illustrated in Figures 1 and 2. Fig. 1
15 illustrates an encapsulation assembly 1 for a plurality of OLED display devices 3 on a substrate 2. The OLED display devices include at least one OLED stack formed on the substrate. The OLED stack or stacks have a conventional construction including a pair of conducting layers (anode and cathode) and an organic stack sandwiched there between. The top conductor layer of the stacks may be a low pinhole density transparent conductor
20 top layer (for example ITO), which forms a first barrier. For an up-emitting OLED device, this top conductor layer acts as a cathode, while for down-emitting devices, this top conductor layer acts as an anode.

The encapsulation assembly of the OLED device of this first embodiment includes a first encapsulation layer 11 and a second encapsulation layer 12. The first encapsulation layer 11 is formed of a dielectric oxide layer and is deposited by ALE or ALD. The
25

second encapsulation layer 12 preferably includes a polymer. In this first embodiment, the oxide layer is formed as the first encapsulation layer so that there is no possibility of moisture permeating from the edges of the display. Optionally on top of encapsulation layer 12, is laid down additional encapsulation layers and color filter means or color changing means (CCM; not shown in the figure). Such color filter means or CCM may be patterned directly on encapsulation layer 12, or preferably on a thin layer of SiO₂ or other dielectric oxide layered on top of layer 12. The color filter or CCM fabrication may use any of a variety of well known wet processing techniques where the layer 12 material is sufficiently resistant to the processing conditions. Optionally, on top of the color filtering or changing means, additional encapsulation layers may be laid down to protect the color filtration or changing elements.

Following production of the plurality of OLED display devices illustrated in Figure 1, the individual OLED display devices 10 are obtained by dicing the assembly of Figure 1. This dicing operation generates individual devices as illustrated in Figure 2, with individual OLED stacks 13 on top of a substrate 2, with encapsulation layer 11 forming a seal with the substrate, and with encapsulation layer 12 protecting layer 11 from mechanical and chemical damage.

A second embodiment of the present invention is illustrated in Figures 3, 4 and 5. Fig. 3 illustrates an encapsulation assembly 20 for a plurality of OLED display devices 3 on a substrate 2. The OLED display devices include at least one OLED stack formed on the substrate. The OLED stack or stacks have a conventional construction including a pair of conducting layers (anode and cathode) and an organic stack sandwiched there between. The top conductor layer of the stacks 3 may be a low pinhole density transparent conductor top layer (for example ITO), which forms a first barrier. For an up-emitting OLED

device, this top conductor layer acts as a cathode, while for down-emitting devices, this top conductor layer acts as an anode.

The encapsulation assembly of this second embodiment includes a first encapsulation layer 21 and a second encapsulation layer 22. The first encapsulation layer 21 is formed of a polymer layer and is patterned to leave exposed a portion of the substrate surface in between the individual OLED devices. Such patterning may be achieved by any well-known, conventional means, including shadow masking before layer formation and ablation (e.g. laser ablation) following layer formation. Figure 5 is a top view of the substrate 2 with the first encapsulation layer 21 of this embodiment shown without a second encapsulation layer laid down over it. The dashed lines 25 in Figure 5 indicate where the substrate would be cut as part of the dicing operation following completion of the encapsulation assembly. The second encapsulation layer 22 in Figure 3 is formed of one or more oxide layers and is deposited by ALE or ALD. In this second embodiment, the oxide layer 22 is formed over both the encapsulation layer 21 and the exposed portions of the substrate 2. The areas of oxide layer 22 that are laid down over the exposed portions of the substrate 2 form a seal and barrier to water so that there is much less possibility of moisture permeating from the edges of the display. Optionally on top of encapsulation layer 22, is laid down a third encapsulation layer 23, preferably formed of one or more polymer layers to provide chemical and mechanical protection to the device. Optionally, on top of this third encapsulation layer 23 is laid down color filter means or CCM (not shown in the figure); this color filter means or CCM is more preferably laid down on top of an SiO₂ or other oxide layer (not shown) laid on top of layer 23. Such color filter means or CCM may be patterned directly on encapsulation layer 23 or on the additional SiO₂ or other oxide layer using any well known wet processing technique where the layer 23 or the additional SiO₂ or other oxide layer material is sufficiently resistant to the proc-

essing conditions. Optionally, on top of the color filtering or changing means, additional encapsulation layers may be laid down to protect the color filtration or changing elements.

Following production of the plurality of OLED display devices illustrated in Figure 3, the individual OLED display devices 30 of Figure 4 are obtained by dicing assembly 20 of Figure 3. The individual devices illustrated in Figure 4 have individual OLED stacks 13 on top of a substrate 2, with encapsulation layer 22 forming a seal with the substrate, and with optional encapsulation layer 23 protecting layer 21 from mechanical and chemical damage.

For a high resolution display device, the actual number of stacks 13 in either embodiment will be much greater than that illustrated in the figures, and for a full color display, can reach 4 to 5 million stacks per display. Furthermore, the figures illustrating particular embodiments show rectangular devices, with orthogonal patterning in some cases; the present invention works equally well with other OLED shapes and layout patterns (for example, circular and elliptical) and methods for fabricating such devices are well known.


The use of an oxide layer that is highly conforming and that can be deposited at a temperature low enough for the OLED layers to survive is ideal. The oxide layer preferably is formed from Al_2O_3 or SiO_2 , and most preferably from Al_2O_3 . The thickness of the layer should be high enough to provide a moisture barrier, but low enough to ensure high light transmission. Al_2O_3 layers are typically around 500 Å thick, but can range from 200 to 750 Å, and preferably from 400 to 600 Å. The present invention, however, is not limited to Al_2O_3 and SiO_2 ; rather, other dielectric oxides (for example TiO_2 , ZrO_2 , MgO , HfO_2 , Ta_2O_5 , and multilayer oxides such as aluminum titanium oxide and tantalum hafnium oxide, etc.) having similar properties and conformity may be used as the oxide layer.

The oxide layer is preferably deposited using Atomic Layer Epitaxy (ALE) or Atomic Layer Deposition (ALD) processing, which provide a highly conformal oxide layer that can be deposited without any energetic particles impinging the OLED surface. A low temperature ALD deposition process (approximately 100-120 °C) provides a good

5 conformal coating of an oxide such as Al_2O_3 and SiO_2 . This oxide layer then forms the primary moisture barrier layer. However, such oxides are sometimes attacked by highly basic chemicals, which may be used during the color filter processing.


In order to protect the oxide layer from any kind of chemical attack, a layer deposited at or below room temperature of highly chemically resistant polymer material may be

10 used. Preferred polymers for this layer are the parylenes. The chemical inertness and the ease of deposition of parylenes are well known. Furthermore, parylenes form highly conformal coatings that help in covering any stray particles and pinholes. Parylene coating is a room temperature deposition process that does not require any ultraviolet curing. The three standard parylenes are parylene N, parylene C and parylene D:



15 While any parylene is suitable for the polymer layer of the devices of the present invention, parylene C is preferred because it is lowest of the three in oxygen permeability and moisture vapor transmission. Parylenes are deposited using standard techniques, starting from a dimeric form diparaxylylene (abbreviated DPX, DPX-C and DPX-D for parylene

20 N, parylene C and parylene D, respectively). The dimer is evaporated and sent through a pyrolysis zone where the dimer dibenzyl bonds homolyze to form highly-reactive monomer species as illustrated below for parylene C:



The monomers then travel to the deposition site, where they condense and polymerize on the device on contact. Optionally, and preferably for purposes of the present invention, a well-known adhesion promoter such as trichlorosilane or γ -methacryloxypropylene-
 5 trimethoxysilane may be vapor deposited on the device prior to deposition of the parylene.

The present invention, however, is not limited to parylenes for the polymer layers. Any conformal, chemically resistant polymer with suitable barrier properties may be used, as long as it polymerizes on contact, near, at or below room temperature. In particular, suitable polymers are those that may be formed from vapor phase monomer species that
 10 will condense and polymerize on a surface at a temperature below about 40 °C, and preferably at room temperature (approximately 25 °C). For example, polymers laid down using plasma-enhanced polymer deposition techniques as disclosed in United States Patent Application Nos. 09/212,780 and 09/212,774, both filed on December 16, 1998, and in International Patent Application Publications WO 35605 and WO 35604, both published
 15 June 22, 2000, are also suitable for the polymer layer of the present invention.

The encapsulation assembly of present invention will now be illustrated by way of a non-limiting example.

An active matrix silicon wafer layered with a plurality of OLED devices and maintained under an essentially oxygen and moisture free (less the 1 ppm) nitrogen atmosphere
 20 is placed in the load chamber of an ASM Microchemistry Pulsar 2000 ALCVD apparatus with attached IN-USA ozone generator. The load chamber is then evacuated to a pressure

of 0.1 millitorr. The wafer is then moved from the load chamber into the reactor chamber of the ALCVD device. The reactor chamber is then evacuated to a pressure of 0.001 millitorr and then continuously purged with nitrogen at 400 sccm. The wafer and reactor chamber are then heated to 100 °C and maintained at that temperature during the entire deposition process. Ozone is then introduced into the reactor chamber at 132 grams per normalized cubic meter (GNM3; oxygen flow rate on the IN-USA generator set to 150 sccm) with an ozone pulse duration of 0.5 sec, followed by a purge (nitrogen alone) for 0.5 sec. Trimethyl aluminum (TMA) gas is then introduced into the chamber for 0.1 sec with a nitrogen flow in the TMA source line of 400 sccm and a TMA source line pressure of 240 Torr. The TMA reacts and deposits an atomic layer of Al_2O_3 on the active matrix silicon wafer layered with a plurality of OLED devices. The reactor chamber is then purged again with nitrogen for 0.2 sec. The series of steps beginning with the ozone pulse is then repeated 800 times to lay down subsequent atomic layers of Al_2O_3 to build up an overall layer thickness of approximately 500 Å (approximate growth rate of 0.54 – 0.59 Å/cycle).

The active matrix silicon wafer layered with a plurality of OLED devices and layered with Al_2O_3 is removed from the ALCVD apparatus and transferred into the deposition chamber of a Specialty Coating Systems Model 2060V deposition apparatus with *in situ* adhesion promoter capability. The pyrolysis furnace intermediate between the first and deposition chambers is heated to and maintained at a temperature of 680 °C. A 2.5 g sample of DPX-C in an aluminum boat is introduced into the first chamber of the apparatus, and 1 mL sample of A-174 (available from Specialty Coating Systems) is loaded into the *in situ* adhesion promoter furnace. The entire system is then evacuated to a pressure of 1 millitorr and the adhesion promoter furnace is heated to 190 °C. and held at that temperature until the deposition chamber pressure returns to 1 millitorr. The first chamber temperature is then raised to 150 °C. The DPX-C dimer evaporates and passes into the

pyrolysis furnace where it is pyrolysed to monomer, which passes into the deposition chamber. The monomer deposits and polymerizes as parylene C on the active matrix silicon wafer layered with a plurality of OLED devices layered with Al_2O_3 .

The active matrix silicon wafer layered with a plurality of OLED devices layered
5 with Al_2O_3 and parylene C layers is then transferred into an Ulvac Model MMI electron beam evaporator into the source crucible of which has been loaded SiO_2 . The SiO_2 is premelted and then evaporated at a beam energy of 6.1 kV at 0.29 amperes at a pressure of 0.001 millitorr. The finished assembly is then placed in an oven under ambient pressure nitrogen gas for 30 minutes. This SiO_2 layer provides a hard surface for color filter or
10 CCM fabrication and avoids scumming by the parylene layer.

It will be apparent to those skilled in the art that various modifications and variations may be made in the preparation and configuration of the present invention without departing from the scope and spirit of the present invention. For example, additional protection may be provided by patterning an organic top layer (e.g. laser ablate parylene or
15 photo process O_2 plasma), ALE or sputter inorganic (e.g. 500 Å of Al_2O_3), and a second layer of parylene. After processing and gluing with cover glass (e.g. epoxy) O_2 plasma can be used to remove polymer, chemical etch (e.g. phosphoric acid) can be used to remove Al_2O_3 using cover glass and adhesive as a mask. Thus, it is intended that the present invention covers the modifications and variations of the invention, provided they come
20 within the scope of the appended claims and their equivalents.

Various references have been cited above, all of which are incorporated by reference in their entireties as though fully set forth.

CLAIMS

1. An organic light emitting diode display device comprising a substrate, at least one organic light emitting diode device formed thereon, and an encapsulation assembly formed over the substrate and the at least one organic light emitting diode device, the encapsulation assembly comprising: a first encapsulation oxide layer comprising a dielectric oxide, wherein the dielectric oxide of the encapsulation oxide layer lies over and in direct contact with both the substrate and the at least one organic light emitting diode device; and a second encapsulation layer, wherein the second encapsulation layer covers the first encapsulation layer.
2. An organic light emitting diode display device comprising a substrate, at least one organic light emitting diode device formed thereon, and an encapsulation assembly formed over the substrate and the at least one organic light emitting diode device, the encapsulation assembly comprising: a first encapsulation oxide layer comprising a dielectric oxide deposited using a process selected from the group consisting of ALE and ALD, wherein the dielectric oxide of the first encapsulation oxide layer lies over and is in direct contact with both the substrate and the at least one organic light emitting diode device; and a second encapsulation layer comprising a polymer, wherein the second encapsulation layer covers the first encapsulation layer.
3. The organic light emitting diode display device according to Claim 2, wherein the polymer of the second encapsulation layer comprises a parylene.
4. The organic light emitting diode display device according to Claim 3, wherein the parylene is selected from the group consisting of parylene N, parylene C, and parylene D.
5. The organic light emitting diode display device according to Claim 2, wherein the second encapsulation polymer layer comprises parylene C.

6. The organic light emitting diode display device according to Claim 2, wherein the first encapsulation oxide layer comprises a dielectric oxide selected from the group consisting of Al_2O_3 , SiO_2 , TiO_2 , ZrO_2 , MgO , HfO_2 , Ta_2O_5 , aluminum titanium oxide, and tantalum hafnium oxide.
- 5 7. The organic light emitting diode display device according to Claim 3, wherein the first encapsulation oxide layer comprises a dielectric oxide selected from the group consisting of Al_2O_3 , SiO_2 , TiO_2 , ZrO_2 , MgO , HfO_2 , Ta_2O_5 , aluminum titanium oxide, and tantalum hafnium oxide.
- 10 8. The organic light emitting diode display device according to Claim 4, wherein the first encapsulation oxide layer comprises a dielectric oxide selected from the group consisting of Al_2O_3 , SiO_2 , TiO_2 , ZrO_2 , MgO , HfO_2 , Ta_2O_5 , aluminum titanium oxide, and tantalum hafnium oxide.
- 15 9. The organic light emitting diode display device according to Claim 2, wherein the first encapsulation oxide layer comprises a dielectric oxide selected from the group consisting of Al_2O_3 and SiO_2 .
10. The organic light emitting diode display device according to Claim 3, wherein the first encapsulation oxide layer comprises a dielectric oxide selected from the group consisting of Al_2O_3 and SiO_2 .
- 20 11. The organic light emitting diode display device according to Claim 4, wherein the first encapsulation oxide layer comprises a dielectric oxide selected from the group consisting of Al_2O_3 and SiO_2 .
12. The organic light emitting diode display device according to Claim 2, wherein the dielectric oxide of the first encapsulation oxide layer comprises Al_2O_3 .
- 25 13. The organic light emitting diode display device according to Claim 3, wherein the dielectric oxide of the first encapsulation oxide layer comprises Al_2O_3 .

14. The organic light emitting diode display device according to Claim 4, wherein the dielectric oxide of the first encapsulation oxide layer comprises Al_2O_3 .

15. An organic light emitting diode display device comprising a substrate, at least one organic light emitting diode device formed thereon, and an encapsulation assembly formed over the substrate and the at least one organic light emitting diode device, the encapsulation assembly comprising: a patterned first encapsulation layer wherein the pattern of the first encapsulation layer leaves a perimeter of the substrate exposed around the at least one organic light emitting diode device; a second encapsulation layer comprising an oxide selected from the group consisting of an ALE dielectric oxide and an ALD dielectric oxide, wherein the second encapsulation layer covers both the exposed perimeter of the substrate and the first encapsulation layer.

16. The organic light emitting diode display device according to Claim 15, wherein the first encapsulation layer comprises a polymer.

17. The organic light emitting diode display device according to Claim 16, wherein the polymer comprises a parylene.

18. The organic light emitting diode display device according to Claim 17, wherein the polymer comprises a polymer selected from the group consisting of parylene N, parylene C, and parylene D.

19. The organic light emitting diode display device according to Claim 18, wherein the polymer comprises parylene C.

20. An upwardly emitting organic light emitting diode display device comprising a substrate, at least one organic light emitting diode device formed thereon, and an encapsulation assembly formed over the substrate and the at least one organic light emitting diode device, the encapsulation assembly comprising: a first encapsulation oxide layer comprising Al_2O_3 deposited using a process selected from the group consisting of ALD and ALE, wherein the first encapsulation oxide layer lies over and is in direct

wherein the first encapsulation oxide layer lies over and is in direct contact with both the substrate and the at least one organic light emitting diode device; and a second encapsulation polymer layer, wherein the second encapsulation layer comprises parylene C and covers the first encapsulation layer.

5 21. The organic light emitting diode display device according to Claim 20 further comprising a layer of SiO_2 , wherein the layer of SiO_2 lies over and covers the second encapsulation polymer layer.

22. An upwardly emitting organic light emitting diode display device comprising a substrate, at least one organic light emitting diode device formed thereon, and an
10 encapsulation assembly formed over the substrate and the at least one organic light emitting diode device, the encapsulation assembly comprising: a first encapsulation oxide layer consisting essentially of Al_2O_3 deposited using a process selected from the group consisting of ALE and ALD, wherein the Al_2O_3 of the first encapsulation oxide layer lies over and is in direct contact with both the substrate and the at least one organic light
15 emitting diode device; and a second encapsulation polymer layer, wherein the second encapsulation layer consists essentially of parylene C and lies over and covers the first encapsulation polymer layer.
23. The organic light emitting diode display device according to Claim 22 wherein the Al_2O_3 is deposited using ALD.

24. The organic light emitting diode display device according to Claim 23 further
20 comprising a third encapsulation layer consisting essentially of SiO_2 , wherein the third encapsulation layer lies over and covers the second encapsulation polymer layer.

25. A method of encapsulating an organic light emitting diode display device, wherein the organic light emitting diode display device comprises a substrate, and at least one organic light emitting diode device formed thereon, the method comprising the steps
25 of:

depositing a first encapsulation dielectric oxide layer using a method selected from the group consisting of ALE and ALD, wherein the encapsulation dielectric oxide layer lies over and in direct contact with both the substrate and the at least one organic light emitting diode device; and

5 depositing a second encapsulation layer, wherein the second encapsulation layer covers the first encapsulation layer.

26. A method of encapsulating an organic light emitting diode display device, wherein the organic light emitting diode display device comprises a substrate, and at least one organic light emitting diode device formed thereon, the method comprising the steps
10 of:

depositing a first encapsulation dielectric oxide layer using a method selected from the group consisting of ALE and ALD, wherein the first encapsulation oxide layer lies over and is in direct contact with both the substrate and the at least one organic light emitting diode device; and

15 depositing a second encapsulation polymer layer, wherein the second encapsulation layer covers the first encapsulation layer.

27. The method according to Claim 2, wherein the step of depositing the oxide layer uses ALD.

28. The method according to Claim 26, wherein the step of depositing the oxide
20 layer uses ALD.

29. The method according to Claim 26, wherein the step of depositing the second encapsulation polymer layer is performed with each of the substrate, the at least one organic light emitting device thereon and the first dielectric oxide encapsulation layer at room temperature.

25 30. The method according to Claim 26, wherein the step of depositing the second

encapsulation polymer layer further comprises a step of forming vapor phase monomer species able to condense and polymerize on the first dielectric oxide encapsulation layer at a temperature less than about 40 °C.

1/3




Figure 1




Figure 2




Figure 3




Figure 4




Figure 5

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 01/09623

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 H01L51/20

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 H01L H05B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ, IBM-TDB, INSPEC, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X A	WO 00 08899 A (UNIX CORP) 17 February 2000 (2000-02-17) page 11, line 22 -page 13, line 28; figures 1-3 --- -/-	1 2,6,9, 12,15, 20,22, 25,26

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

20 July 2001

Date of mailing of the international search report

27/07/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

De Laere, A

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 01/09623

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 1995, no. 10, 30 November 1995 (1995-11-30) -& JP 07 169567 A (IDEMITSU KOSAN CO LTD), 4 July 1995 (1995-07-04) abstract	1
A	----	2,6,9, 12,15, 20,22, 25,26
X	EP 0 871 320 A (HEWLETT PACKARD CO) 14 October 1998 (1998-10-14) column 5, line 56 -column 6, line 18	1,2,6,9
A	US 5 693 956 A (LEE HSING-CHUNG ET AL) 2 December 1997 (1997-12-02) column 2, line 65 -column 3, line 27	1-3,6,7, 9,10,12, 13,20, 22,25,26
A	"PACKAGING AN ORGANIC LIGHT EMITTING DIODE" RESEARCH DISCLOSURE, KENNETH MASON PUBLICATIONS, HAMPSHIRE, GB, no. 416, December 1998 (1998-12), page 1620 XP000834092 ISSN: 0374-4353 the whole document	1-3, 15-17
A	DE 198 53 598 A (SAMSUNG ELECTRONICS CO LTD) 10 February 2000 (2000-02-10) column 1, line 1-39 column 6, line 21-45	1,2,6,9, 12,22, 23,25-30
A	US 5 374 570 A (WATANABE JUN-ICHI ET AL) 20 December 1994 (1994-12-20) abstract column 11, line 21-29	1,2,6,9, 12,22, 23,25-30
A	EP 0 903 590 A (HAMAMATSU PHOTONICS KK) 24 March 1999 (1999-03-24) abstract column 5, line 11 -column 6, line 11	1-11, 15-24

INTERNATIONAL SEARCH REPORT

Information on patent family members

National Application No

PCT/US 01/09623

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 0008899 A	17-02-2000	AU 5334999 A	28-02-2000
JP 07169567 A	04-07-1995	JP 7169567 T	04-07-1995
EP 0871320 A	14-10-1998	US 5872355 A	16-02-1999
		JP 10308276 A	17-11-1998
US 5693956 A	02-12-1997	NONE	
DE 19853598 A	10-02-2000	CN 1244598 A	16-02-2000
		GB 2340508 A	23-02-2000
		JP 2000054134 A	22-02-2000
US 5374570 A	20-12-1994	JP 2100061 C	22-10-1996
		JP 2246161 A	01-10-1990
		JP 8024191 B	06-03-1996
		CA 2011627 A,C	17-09-1990
		DE 69020012 D	20-07-1995
		DE 69020012 T	26-10-1995
		EP 0387892 A	19-09-1990
		KR 9308537 B	09-09-1993
EP 0903590 A	24-03-1999	AU 5878898 A	08-09-1998
		JP 3077941 B	21-08-2000
		CA 2260041 A	20-08-1998
		CN 1220732 A	23-06-1999
		CN 1220732 T	23-06-1999
		WO 9836291 A	20-08-1998
		JP 2000284053 A	13-10-2000